

PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD. A.B.N. 92 001 807 245 P.O. Box 312, Neutral Bay. NSW 2089 Australia 59 Moxon Road, Punchbowl NSW Ph: 61 2 9708 2200 Fax: 61 2 9796 3069 Email: norglass@bigpond.net.au www.norglass.com.au



PRODUCT: SLIP RESISTANT AGENT

DESCRIPTION: A uniform granular polypropylene particle for increasing traction in coatings.

USES: Stairs, Paths, Ramps, Driveways, pool areas.

PROPERTIES (at 20°C)

COLOUR:	White
ΤΟΧΙΟΙΤΥ:	Non Hazardous Substance
FINISH:	Textured
COVERAGE:	50g per litre of paint
DRYING TIME:	N/A
RECOATING:	N/A
POT LIFE:	N/A
POT LIFE: MIXING RATIO:	N/A 50g per litre in paint – 15g per litre in clears
MIXING RATIO:	50g per litre in paint – 15g per litre in clears
MIXING RATIO: THINNING:	50g per litre in paint – 15g per litre in clears N/A

CLEAN UP: As specified for the coating medium

U.N. NUMBER: N/A

- **DESCRIPTION:** A granulated powder to provide traction when mixed into low sheen or matte paint/clear finishes. Note. Do not add this product to gloss finishes as the result will be extremely slippery when wet. Norglass Slip Resistant Agent will not settle after mixing but should be stirred before application. At the rate of 50 grams per litre the texture will be optimized, but more or less can be added as desired. When used in clear coatings the ratio of 15 grams per litre should not be exceeded. At that ratio it will not detract from the clear finish.
- **PREPARATION:** Refer to the coating specification
- **DIRECTIONS FOR USE:** Mix the product into the can of matte paint or clear slowly, and continue stirring until thoroughly blended. Then pour into a paint tray. Use a short nap paint roller for best results. Confine the use of a paint brush to edges only.
- **APPLICATION:** To be added to the selected coating in the determined ratio
- TRANSPORTATION: Non Hazardous
- PRECAUTIONS: N/A

FIRST AID: If swallowed DO NOT induce vomiting, give a glass of water or milk. Should not cause harm if swallowed. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and consult a doctor if irritation persists. Remove contact lenses if present and easy to do and continue rinsing. In case of skin contact, remove contaminated clothing and wash skin thoroughly. If breathing difficulty arises remove to fresh air. Apply artificial respiration if not breathing.

SPECIAL INSTRUCTIONS: N/A