

PRODUCT DATA SHEET

NORGLASS LABORATORIES PTY.LTD.

A.B.N. 92 001 807 245

P.O. Box 312, Neutral Bay. NSW 2089 Australia

59 Moxon Road, Punchbowl NSW

Ph: 61 2 9708 2200 Fax: 61 2 9796 3069

Email: norglass@bigpond.net.au

www.norglass.com.au



MICROSHIELD TRADITIONAL MARINE SPAR VARNISH

DESCRIPTION: A clear, low odour, high gloss urethane/alkyd blend with high levels of state of the art inhibitors and stabilizers for maximum exterior protection.

USES: Panelling, doors, outdoor furniture, railings, general bright work on boats and all areas not subjected to heavy traffic.

PROPERTIES (at 20°C)

COLOUR: Light Amber

TOXICITY: See Precautions

FINISH: High Gloss

COVERAGE: Up to 12sqm per litre

DRYING TIME: Touch dry in 3 hours

RECOATING: After 16 hours at 50% relative humidity

POT LIFE: N/A

MIXING RATIO: N/A

THINNING: Not normally recommended, but up to 5% Weatherfast Brushing Thinner can be added to improve flow in hot weather. Use up to 20% Weatherfast Spraying Thinner when spraying.

WEIGHT/LITRE: 0.900kg

VOLUME SOLIDS: 55%

FLASH POINT:	32°C
CLEAN UP:	WEATHERFAST BRUSHING THINNER
U.N. NUMBER:	1263
PREPARATION:	New Bare Timber must be dry, well sanded and have the dust particles within the grain removed by paper towel soaked in NORCLEAN-PLUS. Previously varnished timber (in good condition) should be sanded thoroughly to a flat state then wiped over with a paper towel dampened with NOR-CLEAN PLUS. Cracked or peeling varnishes must be totally removed back to a clean dry timber state.
APPLICATION:	The first coat should be applied by brush to work the product into the timber surface. Thinning the first coat is not normally recommended, but if carried out care must be taken to allow additional time for drying due to the added solvents (24hrs minimum). Very light sanding (with the grain) between a further 3 coats should be a reasonable base structure for finishing. Following this, a minimum of a further 2 coats should be considered essential where exposed to long periods of sunlight.
TRANSPORTATION:	DG Class 3 HAZCHEM 3Y P.G. III SIZES: 4litre, 2 litre, 1 litre and 500ml
PRECAUTIONS:	Provide adequate ventilation during use. Keep away from naked flame and do not smoke. Do not use in damp conditions where humidity exceeds 70% or in temperatures below 10°C.
FIRST AID:	If poisoning occurs call a doctor or Poisons Information Centre (Aust) on 131126 or (NZ) 0800 764 766 and have label information ready. If swallowed DO NOT induce vomiting. Give large quantities of water or milk. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and consult a doctor. Remove contact lenses if present and easy to do and continue rinsing. In case of skin contact, remove contaminated clothing and wash skin thoroughly. If breathing difficulty arises remove to fresh air. Apply artificial respiration if not breathing.
SPECIAL INSTRUCTIONS:	N/A